

REMARKS

The Office Action of April 8, 2004 has been carefully reviewed. Claims 1-14 and 16-24 are pending in the application. Claim 1 has been amended herein to delete formula XV and formula XXXIX. Applicants respectfully acknowledge that claim 14 has been allowed. Claim 1-6, 10-13, 16-20 and 24 are rejected and claims 7-9 and 21-33 have been objected to in the Office Action.

More specifically, claims 1-6, 10-13, 16-20, and 24 are rejected under the judicially created doctrine of obviousness-type double patenting as being unpatentable over claims 1-5, 15, 16, 19, 20, 22, and 23 of U.S. Patent No. 6,297,329. The conflicting patent is commonly owned and a terminal disclaimer is submitted herein to overcome this rejection.

Claims 10, 11, and 16-19 stand rejected under 35 U.S.C. 102(b) as being anticipated by Hall et al. (U.S. Patent No. 4,405,798). This rejection is respectfully traversed.

Hall describes the preparation of (meth)acryloyl-functional bicyclic orthoester monomers. These monomers may be hydrolyzed and homopolymerized or copolymerized to provide resins. If the resins are of low molecular weight, these resins can impart advantageous properties to coating compositions. Polymerization is carried out under the influence of azobisisobutyronitrile (AIBN) initiator. AIBN is a well known radical generating initiator. During radical polymerization the (meth)acrylic double bonds are depleted to form the polymer chain. This is general knowledge and can be inferred from the textbook "*Introduction to Paint Chemistry*" by J. Bentley and G.P.A. Turner at pages 64-65, a copy of which is attached hereto.

Therefore, one skilled in the art would recognize that the resins described by Hall for use in a coating composition are depleted of (meth)acrylic double bonds. Hall does

not teach, suggest, or disclose using the (meth)acryloyl-functional bicyclic orthoester as such in a coating composition as required by the present claim 10. Thus, claim 10, claims 11 and 16-19 depending thereon, and claim 24 directed toward a process of curing the composition according to claim 24 are novel over Hall.

Claims 10, 11, and 16-19 stand rejected under 35 U.S.C. 102(b) as being anticipated by WO 97/31073 and 35 U.S.C. 102(e) as being anticipated by van den Berg et al (U.S. Patent No. 6,297,329 or U.S. Patent No. 6,593,479). This rejection is respectfully traversed.

WO 97/31073 does not disclose a coating composition comprising a compound comprising a bicycle-orthoester group having any of the specific hydroxyl reactive functional groups C according to amended claim 1. Therefore, amended claim 1 and its dependent claims 2-6 are novel over WO 97/31073. Further, nowhere in the Office Action is it specifically pointed out where WO 97/31073 discloses a compound comprising a bicycle-orthoester group having any of the specific hydroxyl reactive functional groups C according to claim 10. Actually, WO 97/31073 does not disclose a coating composition comprising a compound comprising a bicycle-orthoester group having any of the specific functional groups C according to claim 10. Therefore, the present claim 10 and its dependent claims 11, and 16-19, and the process of curing the composition of claim 10 according to claim 24 are considered novel over WO/9731073. Neither van den Berg '329 nor van den Berg '479 overcomes the deficiencies in WO/931073.


It is noted that claims 7-9 and 21-23 are objected to as being dependent upon a rejected base claim, but would be considered allowable if rewritten in independent form. However, as claim 1, as amended herein, is believed to be allowable, claims 7-9 and 21-23, depending upon the amended claim 1, are also believed to be allowable.

Thus, the present invention is considered both novel and non-obvious over the prior art. Applicants respectfully request reconsideration of the rejected claims and a finding that the claims are in condition for immediate allowance.

If an extension of time is required, Applicant herein petitions for such extension of time such that this response is timely. Applicant herein authorizes that any and all charges due be charged to its Deposit Account No. 01-1350.

Respectfully submitted,

HOBEL et al.

A handwritten signature in black ink, appearing to read "Michelle J. Burke". The signature is written in a cursive style with a horizontal line underneath.

Michelle J. Burke
Reg. No. 37,791
Attorney for Applicant

Akzo Nobel Inc.
Intellectual Property Dept.
7 Livingstone Avenue
Dobbs Ferry, NY 10522-3408
(914) 674-5459

Introduction to
Paint Chemistry
and principles of paint technology

J. Bentley

and

G. P. A. Turner

and formerly with ICI Plastics
Group, Yorkshire, UK

Fourth edition

ORDER ON THE INTERNET VIA HTTP, COUNTER, FTP OR EMAIL:
WWW: <http://www.bentley.co.uk>
COUNTER: order@bentley.co.uk
FTP: <ftp://bentley.co.uk>
EMAIL: order@bentley.co.uk
A member of ICI®



CIBAOMAN & HALL

London · Wiesbaden · Bonn · Bonn · Bonn · Bonn · Bonn · Bonn

Published by Chapman & Hall, 2-6 Boundary Row, London SE1 8HN, UK

Chapman & Hall, 2-6 Boundary Row, London SE1 8HN, UK

Chapman & Hall GmbH, Pappelallee 3, 69469 Weinheim, Germany

Chapman & Hall USA, 115 Fifth Avenue, New York, NY 10003, USA

Chapman & Hall Japan, ITP-Japan, Kyowa Building, 3F, 2-2-1
Hirakawacho, Chiyoda-ku, Tokyo 102, Japan

Chapman & Hall Australia, 102 Dodds Street, South Melbourne, Victoria
3205, Australia

Chapman & Hall India, R. Seshadri, 32 Second Main Road, CIT East,
Madras 600 035, India

First edition 1967

Second edition 1980

Third edition 1988

Reprinted 1990, 1991, 1993, 1995

Fourth edition 1998

© 1967, 1980, 1988 G. P. A. Turner; 1998 J. Bentley and G. P. A. Turner

Typeset in 10/12pt Times by Academic & Technical Typesetting, Bristol, UK
Printed in Great Britain by St Edmundsbury Press, Bury St Edmunds, Suffolk

ISBN 0 412 72320 4 (HB) 0 412 72330 1 (PB)

Apart from any fair dealing for the purposes of research or private study, or criticism or review, as permitted under the UK Copyright Designs and Patents Act, 1988, this publication may not be reproduced, stored, or transmitted, in any form or by any means, without the prior permission in writing of the publishers, or in the case of reprographic reproduction only in accordance with the terms of the licences issued by the Copyright Licensing Agency in the UK, or in accordance with the terms of licences issued by the appropriate Reproduction Rights Organization outside the UK. Enquiries concerning reproduction outside the terms stated here should be sent to the publishers at the London address printed on this page.

The publisher makes no representation, express or implied, with regard to the accuracy of the information contained in this book and cannot accept any legal responsibility or liability for any errors or omissions that may be made.

A catalogue record for this book is available from the British Library

Contents

Preface to the fourth edition

Acknowledgements

Names and units

PART ONE: General science

1	Atoms to equations: the basis of chemical reactions	3
2	Inorganic chemistry: acids, bases and salts	17
3	Organic chemistry: alkanes to oils	30
4	Organic chemistry: ethers to isocyanates	47
5	Solid forms: polymers and solid structures	61
6	Colour: physics and chemistry	77

PART TWO: Applied science

7	Paint: first principles	91
8	Pigmentation: pigments and paint making	103
9	Solvents: chemistry and physics of solvents and diluents	118
10	Paint additives: modifying application, curing and appearance	136
11	Lacquers, emulsion paints and non-aqueous dispersions: paints drying by evaporation	150
12	Oil and alkyd paints: paints drying through oxidation	167
13	Thermosetting alkyd, polyester and acrylic paints: paints based on nitrogen resins	187
14	Epoxy coatings: paints based on epoxy resins	203
15	Polyurethanes: isocyanate-based coatings	220

the distinctive property of an amorphous solid is that, when a melt is poured into a tray, or when a solution of the solid is poured upon a surface and the solvent is allowed to evaporate, the resultant solid forms a *continuous* film. Because it has no natural shape of its own, it takes the shape into which it has been cast. A crystalline material would give a discontinuous film, consisting of many hundreds of tiny individual crystals. It is the amorphous continuity that makes the resin film extremely suitable for protecting surfaces.

Polymers


Natural resins are complex mixtures of different substances with fairly large molecules. Nowadays many synthetic resins are used in paints. Synthetic resins have many properties that their natural predecessors did not, but they also consist of mixtures of different molecules, all of which are large.

Synthetic resins are **polymers**. 'Poly-mer' means 'many parts'. A polymer molecule is composed of many smaller parts, contributed by similar or dissimilar molecules, which are joined together until there are hundreds or thousands of atoms in the polymer molecule.


Chain growth polymers

Ethylene (ethene), $\text{CH}_2=\text{CH}_2$, is an example of a simple molecule that can be reacted to form a polymer or become **polymerized**. If ethylene gas is highly compressed (1500 atm), heated to 200°C and allowed to come into contact with a carefully controlled trace of oxygen, the following occurs:

- Oxygen attacks a double bond, opening it. Temporarily a free radical has been created:




- The highly reactive free radical attacks another double bond:




A **chain reaction** has been set in motion and the $-\text{CH}_2-\text{CH}_2-$ unit will repeat itself a thousand times or more in forming a huge molecule of the polymer, polyethylene or polyethene ('polythene').

Polyethylene (polyethene) is not used in paints, because of its marked crystallinity (see below). However, many compounds containing the vinyl ($\text{CH}_2=\text{CH}-$) or vinylidene ($\text{CH}_2=\text{C}<$) group can be polymerized by a free radical route and many of the products are useful in paints, as we shall see, e.g.



vinyl chloride (chloroethene)

PVC (polyvinyl chloride)



vinyl acetate (ethanoyloxy-ethene)

PVAc (polyvinyl acetate)



methyl methacrylate (methyl 2-methyl-propenoate)

PMMA (polymethyl methacrylate, 'Perspex')



PBA (polybutyl acrylate)

butyl acrylate (butyl propenoate)

Usually the **monomer** (as the starting compound is called) is liquid and can be polymerized in bulk or in solution. The **initiator** of polymerization is not oxygen, but some compound which, on heating, decomposes into free radicals, e.g. an organic peroxide (Table 5.1). The first reaction of free radical with a monomer molecule is termed the **initiation step**.

The most frequently encountered peroxides are compounds which decompose at temperatures between 80 and 180°C. They all possess the link $-\text{O}-\text{O}-$ found in the simple inorganic compound hydrogen peroxide, but with one or both hydrogen atoms substituted by other groups as shown on page 66. Those peroxides with only one hydrogen substituted are called **hydroperoxides**, and they are particularly important in the oxidative drying of oils (Chapter 12).

Other compounds used are **azo compounds** with a $-\text{N}=\text{N}-$ bond; azo-diisobutyronitrile (ADIB) is a common example. These compounds decompose as follows:











Table 5.1 Organic peroxides


Attached group(s)	Peroxide type	Comments	Example
1. $2R-\overset{\overset{O}{\parallel}}{C}-$ acyl groups	$R-\overset{\overset{O}{\parallel}}{C}-O-O-\overset{\overset{O}{\parallel}}{C}-R$ diacyl peroxide	R may be aliphatic or aromatic ester of the peracid,	 benzoyl peroxide (dibenzoyl peroxide)
2. $R-\overset{\overset{O}{\parallel}}{C}-$ and $-R'$ alkyl	$R-\overset{\overset{O}{\parallel}}{C}-O-O-R'$ peracid ester	$R-\overset{\overset{O}{\parallel}}{C}-O-O-H$	 <i>tert</i> -butyl perbenzoate
3. $\begin{array}{c} R \\ \diagup \\ C \\ \diagdown \\ R' \end{array}$	 ketone peroxide	or aldehyde peroxide if R' is H	 methyl ethyl ketone peroxide
4. $R-$ and $-H$	$R-O-O-H$ hydroperoxide		 cumene hydroperoxide
5. $2R-$	$R-O-O-R$ dialkyl peroxide		$(CH_3)_3C-O-O-C\cdot(CH_3)_3$ di <i>tert</i> -butyl peroxide

The sequence of growth steps, normally termed **propagation**, of the polymer chain is terminated by one of the following occurrences:

- **Combination.** An encounter between two polymer free radicals which satisfy one another's free valencies:



- **Disproportionation.** A similar encounter, in which one free radical removes a hydrogen atom from the other to become a saturated compound. The double radical rearranges to an unsaturated compound; neither free radical survives:




- **Chain transfer.** The polymer free radical is satisfied by the removal of a monovalent atom (usually hydrogen) from another molecule:




One polymer chain is ended, but another begins, as a result of the creation of a new free radical. Hence the chain reaction is 'transferred' to another molecule. The hydrogen atom may be removed from:

- another monomer molecule;
- a solvent molecule;
- another polymer molecule, in which case further polymer will grow from the transfer site resulting in a branched rather than a linear structure;
- a compound called a **chain transfer agent**, specially included in the preparation for this purpose.

A reactive material which may also be present but which hinders or prevents polymerization taking place is known as an **inhibitor**. Hydroquinone (benzene-1,4-diol),



and other phenolic materials are effective in reacting with free radicals to destroy their free radical nature, e.g.



where X is an alkyl group and the inhibitor a trialkyl phenol.

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.